

DORTHZ STAB

COLOUR STABILISER / EQUALISER

1. PRESENTATION

Solvent-based liquid primer, pigmented or colourless, used as a **colour equaliser and stabiliser** for all varieties of wood.

2. ADVANTAGES

- Stabilises, saturates et equalises colours in a single operation.
- Resists yellowing.
- Prevents the blueing and greying of wood (pigmented version).
- Allows the wood to breathe.
- Straight and simple application.
- High covering capacity.
- Very economical.
- Can be coated over (paint, varnish, wood stain...) after 24 hours.
- Deep penetrating protection for wood (over the 3-month warranty period).

3. AREAS OF APPLICATION

- Elements made of different wood varieties.
- Woods of different ages.

4. INSTRUCTIONS

Substrate preparation:

Substrates must be sound, clean, free of oil or grease.

With woods having moisture contents of less than 18% on the outside and 12% on the inside.

Preparatory work:

Loose particles, dust, etc. must be removed by brushing, scraping or washing.

Remove all traces of fat.

Remove old coats of loose paint.

New woods: remove dust, cover the heads of nails and screws with putty.

Exuding exotic woods: degrease using **NETT BROSS**, replace wiping cloths often. (Afzelia: wash with ammonia).

Woods already attacked or suspicious shall be pretreated using **XYLO DORTHZ** or **XYLO MUHC 50**.

These recommendations cannot replace the appropriate determination of the nature and condition of the substrates to be painted.

Implementation:

DORTHZ STAB is ready to use.

Shake well before use and during use.

Application conditions	: As per standard NF P 74-201-1
Application temperature	: Between +5°C and +35°C
Hygrometry	: Outdoors, ≤ 80% relative humidity : Indoors, ≤ 65% relative humidity
Application equipment	: Brush, roller, airless spray gun
Cleaning of the equipment	: NETT BROSS (do not allow to dry)

5. CHARACTERISTICS

Appearance in container	: Semi-gelled liquid
Film appearance	: Satin
Density	: $0.81 \pm 0.05 \text{ g.cm}^{-3}$
Dry content	: $15 \pm 2\%$ by weight
VOC (Directive 2004/42/EC)	: EU limit value for this product (cat. A/d)*: 750 g/L (2010). This product contains 690g/L maximum.
Yield	: 7 to 15 m ² /L per coat depending on the porosity of the substrate.
Drying (20°C – 65% RH)	: Touch dry in 2 hours Coating over after 24 hours
Coating over	: Within 3 months maximum
Colours	: As per DORTHZ STAB colour chart.
Shelf life	: 2 years in its unopened original packaging

(For more information, please refer to paragraph 9 of the safety data sheet).

DORTHZ STAB

COLOUR STABILISER / EQUALISER

6. SAFETY OF USE

- See the product's Safety Data Sheet at www.quickfds.fr.
- Store away from frost.

DORTHZ STAB colour chart:

221 – Colourless



223 – Light oak

The details provided in this Data Sheet are given in good faith, for information purposes only. They shall not in any case constitute a guarantee on our part, or engage our responsibility when using our products. This Data Sheet supersedes all previous versions. Compagnie France Chimie reserves the right to make changes to its products and to this data sheet without prior notice. Our clients shall ensure, before any implementation, that these instructions have not been replaced by a more recent version that takes into account new technical data.

Product solely intended for professional use.

EURO DORTHZ PRODUCTION

42/44 rue Georges Besse — 63100 Clermont-Ferrand — FRANCE
Tel. +33 (0) 4 73 14 40 40 / Fax +33 (0) 4 73 14 40 44
Website: www.dorthz.com